

## STRETCH FOLIE ruční transparent STANDARD

CHARAKTERISTIKA Characteristics	JEDNOTKA Unit	HODNOTA* Values*
<b>TLOUŠŤKA</b> Thickness	[μm]	<b>23 ± 5%</b>
<b>HUSTOTA</b> Density	[g/cm <sup>3</sup> ]	<b>0,918 ± 2%</b>
<b>PRŮTAŽNOST GARANTOVANÁ</b> Pre-stretch Guaranteed (Quality Test Plot) HIGHLIGHT TEST	[%]	<b>120 - 150 ± 10%</b>
<b>PRŮTAŽNOST PŘI PŘETRHNUTÍ</b> Elongation at brake (Ultimate Test Plot) HIGHLIGHT TEST	[%]	<b>&lt; 247</b>
<b>ODOLNOST</b> Puncture test HIGHLIGHT TEST	[kg]	<b>2,03 ± 10%</b>
<b>SÍLA MAXIMÁLNÍ RETENCE</b> Retention Maximum Force HIGHLIGHT TEST	[kg]	<b>1,93 ± 10%</b>
<b>SÍLA RETENCE po stabilizaci zátěže</b> Retention Force HIGHLIGHT TEST	[kg]	<b>1,78 ± 10%</b>
<b>PŘILNAVOST</b> Cling HIGHLIGHT TEST	[g]	<b>max. 31,00 ± 10%</b>
<b>HLADINA ZVUKU</b> Sound level HIGHLIGHT TEST	[dB]	<b>&gt; 90</b>

\* The given parameters values were established on the basis of laboratory tests conveyed in specific conditions. In case the manufacturers recommendations are disobeyed, especially in regard to storage and usage conditions, those parameters may differ from the values assumed in Technical Data Sheet.

*External view of the product: Transparent film without discoloration, tearing, holes, without pressed folds.*

*We hereby certify that this product does not put in danger the life, health, working security and environmental protection.*

*In accordance with the applicable regulation stretch film is not classified as a dangerous product. It does not contain dangerous substances in conformity with EN- 13428 norm and heavy metals, phthalates, chlorine, Bisphenol A i S, mineral oil, tin, tantalum, tungsten, gold.*

*Storage conditions: temperature range +10°C do +25°C, moisture 40%- 70%, no direct sunlight or rainfalls, no smoking, no open flames or sources of ignition in the storage area.*

*Handling: application temperature range -5°C do +30°C regarding seasonality and cling properties.*